

DATA SHEET

207 (HC) EPOXY FAIRING COMPOUND QUICK SET

(Page 1 of 3)

VI-28/11/2014

DESCRIPTION

- A high quality, light weight, high strength filler and fairing compound for smoothing imperfections above or below the water line on steel, cement, aluminium and fibreglass hulls. 207 incorporates hollow spheres for an exceptional finish.

PROPERTIES

- Excellent sag resistance.
- No shrinkage (100% solids).
- High bond strength.
- Excellent sanding properties.
- Smooth consistency when mixed.

CHEMICAL RESISTANCE

- Resistant sea water, most dilute acids and alkalis. Petroleum products and aliphatic solvents.

SURFACE PREPARATION

- **STEEL** : Grit blast to Sa2 ½ (50µ minimum profile).
Prime with 502 Epoxy Zinc Phosphate Primer @ 8 - 10m²/l (30 - 40µ DFT).
- **ALUMINIUM**: Sweep blast or grind with 60 grit disc pads to a ± 50µ profile. Prime with 504 Epoxy Primer @ 5m²/l.
- **FIBERGLASS**: Sand surfaces with 80 – 100 grit sand paper.
- **WOOD** : Sand surface with 80 – 100 grit sand paper.

DATA SHEET

207 (HC) **EPOXY FAIRING COMPOUND QUICK SET**

(Page 2 of 3)

V1-28/11/2014

MIXING INSTRUCTIONS

- Using a spatula mix two parts by volume of base resin (white) with one part activator (green or blue) to a uniform green colour. (Do not Add Thinners). Apply with a trowel or scraper and smooth with epoxy thinners. Allow to cure overnight (8-12 hours) before sanding.

TOXICITY

- Although 207 Epoxy Fairing Compound is relatively non-toxic, it is recommended that the normal precautions in dealing with conventional Epoxy systems are adhered to. Refer to the 16 point Material Safety Data Sheet.

HOW TO SPECIFY

- All surfaces to be prepared primed and faired with 207 Fairing Compound according to the manufacturer's instructions.

DATA SHEET

207 (HC)
EPOXY FAIRING COMPOUND QUICK SET

(Page 3 of 3)

V1-28/11/2014

TECHNICAL DATA

NO. OF COMPONENTS	: 2
COLOUR	: Base : White : Activator : Blue : Mixed : Blue
CONSISTENCY	: Smooth Paste
SAG RESISTANCE	: 20mm @ 25°C
MIXING RATIO (BY VOL)	: 4 Parts Base; 2 Part Activator
POT LIFE	: 25 min @ 25°C
TOUCH DRY (25°C)	: 2 hours
PRACTICAL CURE	: 6 hours
FULL CURE	: 7 Days
COVERAGE	: 1l/m ² /1mm
CLEANER	: W S Cleaner
SHELF LIFE	: 24 months
PACKAGING	: 6 litres

The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the users' responsibility to confirm the currency of product data sheets.