

## TECHNICAL DATA SHEET

## D216 QC SOLVENT FREE EPOXY PRIMER

V2-22/03/2024

### DESCRIPTION

D216 is a low viscosity solvent free crack injection compound and primer for concrete.

### PROPERTIES

- Tensile strength @ 21 °C: 6.2 mPa.
- Compressive strength @ 21 °C: 65 mPa.
- Excellent adhesion and bond strength

### RECOMMENDED AREAS FOR USE

- Solvent free crack injection compound.
- Used as a primer for flooring compounds.
- Laminating resin with good wetting ability.
- Can be mixed with aggregate for tile grouting and epoxy mortars.

<b>COLOUR</b>	: Clear
<b>Nº. OF COMPONENTS</b>	: 2
<b>MIXING RATIO (VOL)</b>	: 2 : 1
<b>CONSISTENCY</b>	: Liquid
<b>VOLUME SOLIDS</b>	: 100%
<b>MIXED DENSITY</b>	: 1.08
<b>PRACTICAL SPREAD RATES</b>	: 4 - 6m <sup>2</sup> /ℓ
<b>POT LIFE @ 25°C</b>	: 30 min
<b>TOUCH DRY @ 25°C</b>	: 4 hrs
<b>HARD DRY @ 25°C</b>	: 24 hrs
<b>FULL CURE</b>	: 7 days
<b>CLEANER</b>	: D701 WSBC
<b>SHELF LIFE</b>	: 12 months
<b>PACK SIZE</b>	: 5 & 15 litres

### CHEMICAL RESISTANCE

Resists most common aggressive chemicals, petroleum products, dilute acids, alkalis, aliphatic solvents and sea water.

### SURFACE PREPARATION

All surfaces must be clean, structurally sound, and free of dust, oil and dirt. Concrete surfaces should be abrasive blasted or acid etched to remove laitance. Moisture content should be below 10%.

### MIXING INSTRUCTIONS

Mix the base and activator in the proportions given using a slow mechanical mixer. Make sure only enough is mixed that can be used within 20 minutes.

### APPLICATION METHOD

Apply by brush or roller.

### TOXICITY

Although D216 is safe, inert and harmless when fully cured, care should be taken to avoid skin contact or inhalation of the uncured components during mixing and application. Refer to the relevant 16-point Safety Data Sheet.

### HOW TO SPECIFY

All surfaces to be suitably prepared and primed with D216 QC Solvent Free Epoxy Primer.

*The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the user's responsibility to confirm the currency of product data sheets.*